

# BIJLARD PVC LIJM FLOOR (PVC FLOOR ADHESIVE)



## PRODUCT DESCRIPTION

PVC LIJM FLOOR is a solvent free PVC and vinyl adhesive based on acrylic dispersion with a very high initial adhesion.

## APPLICATION

For gluing PVC, vinyl and rubber floor coverings in strips and tiles on to the most common substrates. Can also be used as a universal adhesive for all common types of soft and semi-soft floor covering for interior use on floors and walls.

## USE

Apply PVC LIJM FLOOR evenly on a clean, grease-free, smooth and flat substrate using the SQRAPER® 1 (adhesive comb A3), if necessary, level in advance with EGALINE 12 FLOOR. Allow the adhesive to dry until transparent (approx. 40 minutes, apply within max. 240 min). Then lay the floor covering in place and roll it using a heavy roller (approx. 45 kg, working width 42 cm, diameter 11 cm.). Weigh down any raised parts/areas. Avoid any air being trapped under the floor covering. If necessary, roll the ends and seams again after 30 minutes. Wet adhesive residue can be removed using a damp cloth. The indicated processing times are based on a temperature of +20°C and 65% relative humidity.

## IMPORTANT

It must be ensured when gluing that the temperature of the subfloor, the glue, the material to be processed and the processing area are the same. All the materials to be glued, as well as the glue, must be acclimatised in the processing area for at least 48 hours.

The substrate must meet the requirements of ATV DIN 18 365 "Floor covering works", BS CP 8203 & 8204 or comparable national standards. The substrate must be clean, dry, uniform and free of any unevenness and substances that could hinder adhesion. If equalisation is required, please refer to the EGALINE 12 FLOOR technical data sheet. Click [here](#).

If the floor covering is to be laid on underfloor heating, please refer to the Underfloor heating protocol. Click [here](#).

**BIJLARD**®  
**PROFESSIONAL ADHESIVES**

## TECHNICAL INFORMATION

Basic raw material	: acrylic dispersion
Colour	: white, transparent when dry
Solid content	: approx. 58%
pH-value	: 8
Density	: 1.04 kg/m <sup>3</sup>
Viscosity	: 20,000 mPa·s
Open time	: approx. 40 minutes at +20 °C and 65% rel. humidity
Consumption	: approx. 250/350 g/m <sup>2</sup>
Temperature resistance	: from +5 °C to +45 °C
Moisture and frost resistance	: good
Processing temperature	: +10 °C to +25 °C

## SHELF LIFE

PVC LIJM FLOOR can be stored in unopened packaging in a cool, frost-free area for at least 12 months after production. Always use in order of receipt (FIFO).

## CLEANING

Clean tools with water or CITRONEL.

## PACKAGING

10 kg bucket.

**Our processing advice is based on extensive research. We cannot accept any responsibility for the results and/or for any damage incurred in the use of this product due to the great variety of materials and conditions during adhesion. Please do not hesitate to contact us for advice.**

**BIJLARD**®  
**PROFESSIONAL ADHESIVES**