

BIJLARD ACRYL FLOOR



PRODUCT DESCRIPTION

ACRYL FLOOR is a solvent-free PVC and vinyl adhesive based on acrylic dispersion with a very high initial tack.

APPLICATION

For bonding PVC, vinyl, and rubber floor coverings in strips and tiles on most common subfloors. Also suitable as a universal adhesive for all common types of soft and semi-soft floor coverings for indoor use on floors and walls.

APPLICATION METHOD

Apply ACRYL FLOOR evenly using the SQRAPER® A3 on a clean, grease-free, smooth, and level surface. If necessary, level with EGALINE 10A FLOOR beforehand. Allow the adhesive to dry for approx. 20–30 minutes. After drying, apply the floor covering to the subfloor within 1 hour and 15 minutes. After laying, roll the floor covering using a heavy roller (approx. 45 kg, working width 42 cm, diameter 11 cm). Press down any raised areas. Avoid trapping air beneath the floor covering. After 30 minutes, re-roll the butt joints and seams. Remove wet adhesive residues with a damp cloth. The indicated working times are based on +20 °C and 65% relative humidity.

IMPORTANT

During bonding, ensure that the temperature of the subfloor, the adhesive, the material to be applied, and the working environment are equal. All materials to be bonded, as well as the adhesive, must be acclimatized in the processing area for at least 48 hours.

The substrate must comply with the requirements of ATV DIN 18 365 "Flooring works," BS CP 8203 & 8204 or equivalent national standards. The substrate must be clean, dry, homogeneous, and free from irregularities and substances that could impair adhesion. If levelling is necessary, refer to the EGALINE 10A FLOOR data sheet.

For installations over underfloor heating, refer to the Underfloor Heating Start-up Protocol.

BIJLARD®
PROFESSIONAL ADHESIVES

TECHNICAL INFORMATION

Base Material: Acrylic dispersion

Colour: Cream white

Solids Content: approx. 58%

pH Value: 8.5

Density: 1.12 kg/m³

Viscosity: 67.000 mPa·s

Open Time: approx. 30–75 minutes at +20 °C and 65% relative humidity

Consumption: approx. 250–350 grams/m²

Temperature Resistance: from +5 °C to +45 °C

Moisture and Frost Resistance: good

Application Temperature: +10 °C to +25 °C

SHELF LIFE

ACRYL FLOOR can be stored unopened, in a cool and frost-free environment, for at least 12 months after production. Always use in the order of receipt (FIFO).

CLEANING

Clean tools with water or CITRONEL.

PACKAGING

10 kg bucket.

Our application advice is based on extensive research. Due to the wide variety of materials and conditions under which the adhesive is used, we accept no liability for the results obtained and/or any damage arising from the use of the product. We are happy to assist with advice.

BIJLARD®
PROFESSIONAL ADHESIVES